



Year: 01/2010

Reference Standard: **EN 1469**

Product: **Slabs of natural stone for cladding**

Denomination: **Portland Basebed**, Limestone
*Jordans Quarry, Easton Street, Portland,
Dorset, England*

End Uses: **Internal Wall and Ceiling Finishes**

Name and address of the producer: **Albion Stone plc**

Characteristics	Declared values	Test method
Reaction to Fire	Class A1	Without testing (see decision 96/603/EC, as amended)
Flexural Strength	LEV: 3.68 MPa Mean Value: 6.78 MPa Standard Deviation: 0.89	EN 13161
Resistance to Fixings at 75mm thick	LEV: 1,301 N Mean Value: 1,637 N Standard Deviation: 184	EN 13364
Water Vapour Permeability	NPD	EN ISO 12573 or EN 12524
Apparent Density	LEV: 2,122 kg/m ³ HEV: 2,236 kg/m ³	EN 1936